

3M

Scotch-Weld™

Epoxy Adhesive

DP-460 EG

Technical Data

March, 2003

Product Description 3M™ Scotch-Weld™ Epoxy Adhesive DP-460 EG is designed to have lower outgassing and lower ionics than 3M™ Scotch-Weld™ Epoxy Adhesive DP-460. Laboratory testing has shown that Scotch-Weld Epoxy Adhesive DP-460 EG's curing and adhesive performance to be comparable to Scotch-Weld Epoxy Adhesive DP-460.

Application Ideas

- Hard Disk Drive Assembly
- Spindle Motor Assembly
- Magnet Bonding
- E-Block Assembly
- Bearing Cartridge Assembly
- Potting
- Rigidizing

Key Features

- Curing and bonding performance comparable to Scotch-Weld Epoxy Adhesive DP-460
- Total outgassing < 1000 µg/g (via GC/MS, 85°C for 3 hours)
- Siloxane outgassing ≤ 5 µg/g (via GC/MS, 85°C for 3 hours)
- Lower chloride ion content than standard epoxies

Typical Uncured Physical Properties **Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**


Product		Scotch-Weld Epoxy Adhesive DP-460 EG
Viscosity (at 72°F [23°C])	Base Accelerator Mixed	25,000 - 45,000 cps 10,000 - 15,000 cps 15,000 - 25,000 cps
Base Resin	Base Accelerator	Epoxy Amine
Color	Base Accelerator	White Amber
Net Weight (lb/gallon)	Base Accelerator	9.4 9.0
Mix Ratio (B:A)	Volume Weight	2:1 2:0 : 0.96
Worklife (72°F [23°C])		60 minutes

Scotch-Weld™ Epoxy Adhesive DP-460 EG

Curing

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

This adhesive will cure in 24 hours at room temperature. Heating will accelerate the cure and can result in a higher T_g than room temperature curing yields. Curing data is shown in the figure below.



Scotch-Weld™
Epoxy Adhesive
 DP-460 EG

Typical Performance Characteristics¹

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Shear and Peel Strength vs. Cure Temperature/Time

	72°F (23°C) 24 hours	120°F (49°C) 270 minutes	160°F (71°C) 90 minutes	200°F (93°C) 30 minutes	250°F (121°C) 10 minutes
Overlap Shear² (lbf/in²) (ASTM D-1002-72)	> 5000	> 5000	> 5500	> 5500	> 5500
T-Peel³ (lbf/in) (ASTM D1876-61T)	60 ⁴	59 ⁴	43 ⁴	39 ⁵	45 ⁵

¹- See Technical Data Sheet 3M™ Scotch-Weld™ Epoxy Adhesive DP-460 for additional typical performance characteristics.

²-0.060 inch thick, etched aluminum pulled at 0.10 inches/minute.

³-0.032 inch thick, anodized aluminum pulled at 20 inches/minute.

⁴- Cohesive failure mode.

⁵- Adhesive failure mode.

Storage and Shelf Life

Storage: Store 3M™ Scotch-Weld™ Epoxy Adhesive DP-460 EG at 60-80°F (15-27°C) or refrigerate for maximum shelf life.

Shelf Life: Scotch-Weld Epoxy Adhesive DP-460 EG has a shelf life of 12 months in its original container.

Scotch-Weld™

Epoxy Adhesive

DP-460 EG

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550. Address correspondence to: 3M Electronics Markets Materials Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55106. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy

Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability

Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9002

This Electronics Markets Materials Division product was manufactured under a 3M quality system registered to ISO 9002 standards.

3M

Industrial Business
Electronics Markets Materials Division

3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55106



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2003 78-6900-9832-8 (3/03)